



# (ARMORGUARD) ACID CURED 350 WHITE TOPCOAT

## M5623

### PRODUCT DESCRIPTION

35° satin white Armorguard topcoat.

### RECOMMENDED USES

Furniture, kitchen cabinets, and architectural woodwork.

### BENEFITS

- High build satin white finish

#### **Performance**

- Easy spray.
- Good Flow.
- Fast dry.
- Non-yellowing
- Excellent chemical and water resistance
- Superior chemical .
- No reportable formaldehyde
- No recoat window
- VOC compliant in NY and NJ area.

### APPLICATION

- **Catalyst Ratio:** 10 fluid ounce of catalyst 40006 per gallon.
- Do not exceed 4 mils including primer coat.

### SPECIFICATIONS

**Color**..... White

**Gloss**..... 35°

**Mixed Viscosity**..... 18 ± 1 seconds  
#2 Zahn Cup

**Density**..... 8.10 lbs/gal ± 0.1

**Solids By Weight**..... 40% ± 1%

**Solids By Volume**..... 33% ± 1%

**VOC**..... 4.86 lbs/gal 583 gms/lit

**Coverage**..... 525 sq. ft./gal @ 1.0 mil  
dry film thickness

**Recommended Dry Film Thickness**..... 1 - 2 mils

**Pot Life**..... 1 working day, 8-10 hours  
Consult Technical Sales Staff.

